










### LEMZON GRANITO LLP

<b>FORMAT</b>	600X1200mm
<b>THICKNESS (mm)</b>	9
<b>PRODUCT</b>	PORCELAIN
<b>KIND</b>	GLAZED
<b>GROUP</b>	Bia - GL

### APPLICABLE STANDARD ISO 13006 ANNEX G

TESTS		RESULTS	
	UNE-EN ISO 10545-2 <b>DIMENSIONS AND SURFACE QUALITY</b>	DIMENSIONS	COMPLIES WITH THE STANDARD
	UNE-EN ISO 10545-3 <b>WATER ABSORPTION</b>	AVERAGE VALUE (%)	≤ 0,5 %
	UNE-EN ISO 10545-4 <b>MODULUS OF RUPTURE</b>	BREAKING STRENGTH (N) MODULUS OF RUPTURE (N/mm <sup>2</sup> )	1.600 - 2.400 N 35 - 45 N/mm <sup>2</sup>
	UNE-EN ISO 10545-7 <b>SURFACE ABRASION (PEI)</b>	RESULT	PEI 4
	UNE-EN ISO 10545-9 <b>THERMAL RESISTANCE</b>	RESULT	RESISTS
	UNE-EN ISO 10545-11 <b>CRAZING RESISTANCE</b>	RESULT	RESISTS
	UNE-EN ISO 10545-12 <b>FROST RESISTANCE</b>	RESULT	RESISTS
	UNE-EN ISO 10545-13 <b>CHEMICAL RESISTANCE</b>	AMMONIUM CHLORIDE 100 g/l	A
		SODIUM HYPOCHLORITE 20 mg/l	A
		HYDROCHLORIC ACID 3% CITRIC ACID POTASSIUM HYDROXYDE 30 g/l	COMPLIES WITH THE STANDARD
	UNE-EN ISO 10545-14 <b>STAIN RESISTANCE</b>	GREEN AGENT IN LIGHT OIL	5
		IODINE SOLUTION IN ALCOHOL	5
		OLIVE OIL	5